

Test Report

Number: GZHH00544164

Applicant: FLASHBAY ELECTRONICS
BUILDING2, JIXUN INDUSTRIAL PARK, XINJIAO,
DONG'AO VILLAGE, SHATIAN TOWN, HUIYANG
DISTRICT, HUIZHOU CITY, GUANGDONG PROVINCE,
P.R.CHINA

Date: Jul 18, 2024

Sample Description:

Eleven (11) pieces of submitted sample said to be :
Item Name : **Foodware**
Item No. : **Nibbles / NI**
Country of Origin : **China**
Date Sample Received : **May 30, 2024**
Testing Period : **May 30, 2024 ~ Jul 12, 2024**



Tests conducted:

As requested by the applicant, refer to attached page(s) for details.

To be continued




Test Report

Number: GZHH00544164

Conclusion:

<u>Tested sample</u>	<u>Standard</u>	<u>Result</u>
Tested component(s) of submitted sample(s)	Council Europe Resolution AP (2004) 5 on Silicones Used for Food Contact Applications on Overall Migration	Pass
	EU Technical Guide Council of Europe Resolution CM/Res(2013)9 on metals and alloys Used in Food Contact Materials and Articles on specific migration of heavy metal	Pass

Authorized by:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou Branch, Hardlines



Victor T.J. Wang
General Manager



Test Report

Number: GZHH00544164

Tests Conducted

1 Overall Migration Test for Silicones

As per Council Europe Resolution AP (2004) 5 on silicones used for food contact applications, selection of test condition & food simulants by Commission Regulation (EU) No. 10/2011 and its amendments.

I. Test condition:

Aqueous food simulant:	
Test no.	Time and temperature
OM2	10 days at 40 °C

Fatty food simulant:	
Test no.	Time and temperature
OM2	10 days at 40 °C

Tested component	Food simulant	Time(hour)	Temperature(°C)
(1)	10% (v/v) Ethanol	240	40
	3% (w/v) Acetic acid	240	40
	95%(v/v) Ethanol	240	40
	Iso -octane	48	20

II. Test results

Food Simulant	Result(mg/dm ²)			Detection Limit (mg/dm ²)	Limit (mg/dm ²)
	1 st migration	2 nd migration	3 rd migration		
10% (v/v) Ethanol	ND	ND	ND	1	10
3% (w/v) Acetic acid	ND	ND	ND	1	10
95%(v/v) Ethanol	7	7	ND	1	10
Iso -octane	35	3	ND	1	10

ND = Not detected (less than detection limit)

Tested component(s): See component list in the last section of this report.



Test Report

Number: GZHH00544164

Tests Conducted

2 Release Testing on Metals and Alloys Used in Food Contact Materials and Articles

With reference to EU Technical Guide “Council of Europe Resolution CM/Res(2013)9 on metals and alloys Used in Food Contact Materials and Articles”. Migration test was carried out and heavy metal content was determined by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES) and Inductively Coupled Plasma Mass Spectrometer (ICP-MS).

I. Test Condition:
 Temperature: 40 °C Time: 10 days

II. Test Result:
 Food simulant: Citric acid (5 g/L)

Tested component (2) :							
Elements	Result 1 st test (mg/kg)	Result 2 nd test (mg/kg)	Result 1 st test+Result 2 nd test (mg/kg)	Result 3 rd test (mg/kg)	Detection Limit (mg/kg)	7*Limit (mg/kg)	Limit (mg/kg)
Silver (Ag)	ND	ND	ND	ND	0.05	0.56	0.08
Aluminium (Al)	ND	ND	ND	ND	1	35	5
Chromium (Cr)	0.04	ND	0.04	ND	0.02	1.75	0.250
Cobalt (Co)	ND	ND	ND	ND	0.01	0.14	0.02
Copper (Cu)	ND	ND	ND	ND	0.5	28	4
Iron (Fe)	ND	ND	ND	ND	1	280	40
Manganese (Mn)	ND	ND	ND	ND	0.1	12.6	1.8
Molybdenum(Mo)	ND	ND	ND	ND	0.02	0.84	0.12
Nickel (Ni)	ND	ND	ND	ND	0.1	0.98	0.14
Tin (Sn)	ND	ND	ND	ND	10	700	100
Vanadium (V)	ND	ND	ND	ND	0.005	0.07	0.01
Zinc (Zn)	ND	ND	ND	ND	1	35	5
Antimony (Sb)	ND	ND	ND	ND	0.01	0.28	0.04
Arsenic (As)	ND	ND	ND	ND	0.001	0.014	0.002
Barium (Ba)	ND	ND	ND	ND	0.1	8.4	1.2
Beryllium (Be)	ND	ND	ND	ND	0.01	0.07	0.01
Cadmium (Cd)	ND	ND	ND	ND	0.001	0.035	0.005
Lead (Pb)	ND	ND	ND	ND	0.005	0.070	0.010
Lithium (Li)	ND	ND	ND	ND	0.010	0.336	0.048
Mercury (Hg)	ND	ND	ND	ND	0.003	0.021	0.003
Thallium (Tl)	ND	ND	ND	ND	0.0001	0.0007	0.0001
Magnesium(Mg)	ND	ND	ND	ND	1	-	-
Titanium(Ti)	ND	ND	ND	ND	1	-	-



Test Report

Number: GZHH00544164

Tests Conducted

Tested component (3) :							
Elements	Result 1 st test (mg/kg)	Result 2 nd test (mg/kg)	Result 1 st test+Result 2 nd test (mg/kg)	Result 3 rd test (mg/kg)	Detection Limit (mg/kg)	7*Limit (mg/kg)	Limit (mg/kg)
Silver (Ag)	ND	ND	ND	ND	0.05	0.56	0.08
Aluminium (Al)	ND	ND	ND	ND	1	35	5
Chromium (Cr)	0.04	0.02	0.06	ND	0.02	1.75	0.250
Cobalt (Co)	ND	ND	ND	ND	0.01	0.14	0.02
Copper (Cu)	ND	ND	ND	ND	0.5	28	4
Iron (Fe)	ND	1	1	ND	1	280	40
Manganese (Mn)	ND	ND	ND	ND	0.1	12.6	1.8
Molybdenum(Mo)	ND	ND	ND	ND	0.02	0.84	0.12
Nickel (Ni)	ND	ND	ND	ND	0.1	0.98	0.14
Tin (Sn)	ND	ND	ND	ND	10	700	100
Vanadium (V)	ND	ND	ND	ND	0.005	0.07	0.01
Zinc (Zn)	ND	ND	ND	ND	1	35	5
Antimony (Sb)	ND	ND	ND	ND	0.01	0.28	0.04
Arsenic (As)	ND	ND	ND	ND	0.001	0.014	0.002
Barium (Ba)	ND	ND	ND	ND	0.1	8.4	1.2
Beryllium (Be)	ND	ND	ND	ND	0.01	0.07	0.01
Cadmium (Cd)	ND	ND	ND	ND	0.001	0.035	0.005
Lead (Pb)	0.008	ND	0.008	ND	0.005	0.070	0.010
Lithium (Li)	ND	ND	ND	ND	0.010	0.336	0.048
Mercury (Hg)	ND	ND	ND	ND	0.003	0.021	0.003
Thallium (Tl)	ND	ND	ND	ND	0.0001	0.0007	0.0001
Magnesium(Mg)	ND	ND	ND	ND	1	-	-
Titanium(Ti)	ND	ND	ND	ND	1	-	-

ND = Not detected (less than detection limit)

Remark: The submitted sample is a repeated use article. The migration test was carried out three times on the same article. The sum of the results of the first and second tests should not exceed seven times the limit (Result 1st test + Result 2nd test < 7 * limit) and the Result 3rd test shouldn't exceed the limit.

Ratio of food contact surface area to volume of component (2) used to establish the compliance of material or article = 1 dm² : 147 mL.

Ratio of food contact surface area to volume of component (3) used to establish the compliance of material or article = 0.6 dm² : 100 mL.

Tested component(s): See component list in the last section of this report.



Test Report

Number: GZHH00544164

Tests Conducted

Component list:

- (1) Semi-transparent white silicone (sealing ring of lid).
- (2) Silver color 304 stainless steel (box).
- (3) Silver color 304 stainless steel (lid).



End of report

The statements of conformity reported have considered the decision rule agreed, namely that Intertek have taken account of measurement uncertainty as calculated by Intertek, and applied according to ILAC-G8/09:2019 (Non-binary acceptance based on guard band $w = U$) except designation from the customer, regulation or test specification. This decision rule only applies to the numeric test results.

The sample(s) and sample information hereto are provided by the client who shall be solely responsible for the authenticity and integrity thereof. The results shown in this report relate only to the sample(s) tested. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. This report shall not be reproduced unless with prior written approval from Intertek Testing Services Shenzhen Limited, Guangzhou Branch.



Page 6 of 6

